


## TECHNICAL FEATURES

|  |
|--|
| MODEL: <b>MAYFAIR NEGRO MATE</b>   |
| SIZE: <b>6,5x20</b>  |
| THICKNESS(mm):   |
| DATE: <b>09/09/2024</b>  |
| CODE: <b>015.511.1011.01955</b>  |
| GROUP: <b>GRUPO BIa UNE-EN 14411 Anexo G / SASO GSO ISO 13006:2022 Anexo G</b> |
| TILE TYPE: <b>GL</b>   |
| FINISH: <b>MATT</b>  |
| FAMILY: <b>COMPACGLASS-GLAZED PORCELAIN TILES</b>                              |
| NUMBER OF DESIGNS:   |



| TEST   | RESULT  |                                   |
|--|---|-----------------------------------|
| <b>UNE-EN ISO 10545-2</b> DIMENSIONAL FEATURES                   | <b>COMPLIES WITH THE STANDARD</b>                 |                                   |
| <b>UNE-EN ISO 10545-3</b> WATER ABSORPTION                       | <b>&lt;= 0,5 %</b>                                |                                   |
| <b>UNE-EN ISO 10545-4</b> MODULUS OF RUPTURE - BREAKING STRENGTH | <b>&gt;1300 N</b>                                 |                                   |
|  | MODULUS OF RUPTURE - BENDING STRENGTH             | <b>35-45 N/mm2</b>                |
| <b>UNE-EN ISO 10545-6</b> RESISTANCE TO DEEP ABRASION (MM3)      | <b>NOT APPLY</b>                                  |                                   |
| <b>UNE-EN ISO 10545-7</b> RESISTANCE TO SURFACE ABRASION         | <b>-</b>  |                                   |
| <b>UNE-EN ISO 10545-8</b> LINEAR THERMAL EXPANSION               | <b>&lt;7,0 x 10-6 °C-1</b>                        |                                   |
| <b>UNE-EN ISO 10545-9</b> THERMAL SHOCK RESISTANCE               | <b>RESISTS</b>                                    |                                   |
| <b>UNE-EN ISO 10545-11</b> CRAZING RESISTANCE                    | <b>RESISTS</b>                                    |                                   |
| <b>UNE-EN ISO 10545-12</b> FROST RESISTANCE                      | <b>RESISTS</b>                                    |                                   |
| <b>UNE-EN ISO 10545-13</b>                                       | CHEMICAL RESISTANCE - AMMONIUM CHLORIDE 100 G/L   | <b>A</b>                          |
|  | CHEMICAL RESISTANCE - SODIUM HYPOCHLORITE 20 MG/L | <b>A</b>                          |
|  | CHEMICAL RESISTANCE - HYDROCHLORIC ACID 3%        | <b>COMPLIES WITH THE STANDARD</b> |
|  | CHEMICAL RESISTANCE - CITRIC ACID 100 G/L         | <b>COMPLIES WITH THE STANDARD</b> |
|  | CHEMICAL RESISTANCE - POTASSIUM HYDROXYDE 30 G/L  | <b>COMPLIES WITH THE STANDARD</b> |
| <b>UNE-EN ISO 10545-14</b>                                       | STAIN RESISTANCE - GREEN AGENT IN LIGHT OIL       | <b>5</b>                          |
|  | STAIN RESISTANCE - IODINE SOLUTION IN ALCOHOL     | <b>5</b>                          |
|  | STAIN RESISTANCE - OLIVE OIL                      | <b>5</b>                          |

SLIP RESISTANCE

|  | TEST                     |  | RESULT |
|--|--------------------------|--|--------|
|  | <b>UNE 41901:2017 EX</b> | SLIP RESISTANCE (PENDULUM)                                 | -      |
|  | <b>DIN 51130</b>         | CRITICAL ANGLE OF SLIP (INCLINED PLATFORM)                 | -      |
|  | <b>DIN 51097</b>         | CRITICAL ANGLE OF SLIP. WET-LOADED BAREFOOT AREAS          | -      |
|  | <b>BS7976 (PTV) WET</b>  | CLASSIFICATION ACCORDING TO PENDULUM TEST VALUES (PTV) WET | -      |
|  | <b>ANSI A326.3</b>       | DYNAMIC COEFFICIENT OF FRICTION (DCOF) OF RIGID FLOORS.    | -      |

| TEST        |                    | VALOR UPEC |
|-------------|--------------------|------------|
| <b>UPEC</b> | UPEC CERTIFICATION | -          |

**Declaration of Performance:**

[https://www.pamesa.com/ERP/4.0/empresas/151/045/ficheros/t00030006/113/DdP\\_DoP\\_N003CPR2013.pdf](https://www.pamesa.com/ERP/4.0/empresas/151/045/ficheros/t00030006/113/DdP_DoP_N003CPR2013.pdf)

TECHNICAL DEPARTMENT  
PAMESA CERÁMICA